

Paint Specification

RC200 Actuators, incl. RCT

Paint Process Description:

1. Clean and degrease with alcohol, the anodized actuator.
2. Base Temacoat GPL-S primer, wet 120 microns, dry 60 microns. Drying time at +23 °C, RH50 %, minimum 4 hours. For submersion drying time minimum 16 hours.
3. Epoxy top-coat: Temacoat GPL, RAL3003 Red or according to customer request, wet 120 microns, dry 60 microns. Drying time at +23 °C, RH50 %, minimum 5 hours.



We reserve the right to alterations without previous notice.

Rotork Sweden AB
Kontrollvägen 15, SE-791 45 Falun, Sweden
Tel +46 (0)23-587 00, Fax +46 (0)23-587 45,
falun.info@rotork.com

rotork®

2017-08-30 Ref.No 596A / Art.No. 980596